

栢尔斯道弗工业技术（上海）有限公司

低温材料清单

数字牌号	材料名称	执行标准	使用温度
1.1133	20Mn5		-20℃
1.6582	34CrNiMo6	DIN EN 10269	-40℃
1.6580	30CrNiMo8	DIN EN 10269	-40℃
1.5523	19MnB4		-60℃
1.7218	25CrMo4		-60℃
1.7219	26CrMo4		-60℃
1.7225	42CrMo4		-100℃
1.6583	41NiCrMo7-3-2		-100℃
1.5680	X12Ni5	DIN EN 10269	-120℃
2.4952	NiCr20TiAl	DIN EN 10269	-196℃
2.4669	NiCr15Fe7TiAl		-196℃
1.4980	X6NiCrTiMoVB25-15-2	DIN EN 10269	-196℃
1.5662	X8Ni9		-196℃
1.4401	X5CrNiMo17-12-2		-196℃
1.4404	X2CrNiMo17-12-2		-196℃
1.4403	X4CrNi18-12	DIN EN 10269	-196℃
1.4301	X4CrNi18-10		-196℃
1.4948	X6CrNi18-10		-196℃
1.4307	X2CrNi18-9		-196℃
1.4919	X6CrNiMoB17-12-2		-196℃
1.4941	X6CrNiTiB18-10		-196℃
2.4856/UNS N06625/Alloy625	NiCr22Mo9Nb	ASTM B446/B564/E112	-196℃
2.4610/UNS N06455/Alloy C4	NiMo16Cr16Ti	ASTM B 574/B 564	-196℃
2.4605/UNS N06059/Alloy59	NiCr23Mo16Al	ASTM B 574/B 564	-196℃
2.4602/UNS N06022/Alloy C22	NiCr21Mo14W	ASTM B 574/B 564	-196℃
1.6909wk	X5CrMnNiN18-9		-196℃
1.4562/UNS N08031/Alloy31	X1NiCrMoCu32-28-7	ASTM B581/B649	-196℃
HiMo88	A4-80/A4L-80/316L		-200℃
1.4429	X2CrNiMoN17-13-3		-270℃
1.4910	X3CrNiMoBN17-13-3		-270℃
2.4668/UNS N07718/Alloy 718	NiCr19Fe19Nb5Mo3	DIN EN 10269/ASTM B637	-270℃
1.4980/Alloy 286/660A/B/C/D	X6NiCrTiMoVB25-15-2	DIN EN 10269/ASTM 453	-270℃
1.4910	X3CrNiMoBN17-13-3	DIN EN 10269	-270℃
1.4571/AISI316Ti	X6CrNiMoTi17-12-2	DIN EN10088/10272	-270℃
1.4541/AISI321	X6CrNiTiB18-10	DIN EN10088/10272	-270℃
1.4436/AISI 316L	X3CrNiMo17-13-3	DIN EN10088/10272	-270℃
1.4435/AISI 316L	X2CrNiMo18-14-3	DIN EN10088/10272	-270℃
1.4429/AISI 316LN	X2CrNiMoN17-13-3	DIN EN10269/10272	-270℃
1.4306/AISI 306	X2CrNi19-11	DIN EN10088/10272	-270℃